

## TICO® Pipe Grips

Product Code: RC1159

### Product Description

TICO Pipe Grips consist of a U-bolt enclosed in a moulded sleeve made of TICO FR material, engineered for the straightforward and effective clamping of thin-wall pipes. The isolating strip is crafted from a TICO FR Pad isolation strip. The TICO VHT range is produced using a sleeve and pad constructed from TICO VHT material.

### TICO® FR Sleeve

Typical Properties	Value	Method	Uni
Hardness	60 ± 5	ISO 48	°
Density	1.50	ISO 2781	g/cm <sup>3</sup>
Tensile Strength	37.0	ISO 37	kg/cm <sup>2</sup>
Elongation at Break	500	ISO 37	%
Fire Test: - Burn Length - After Burn	120 Nil	Vertical Burn CAA No 8 Indicative 180 Seconds	mm secs
Smoke Index	15.94	NES711	-
Toxicity Index	2.5	NES713	-
Flammability by Temperature	227	NES715	-
Temperature Range	-50°C to +120°C (+150 intermittent)		°C

### TICO® FR Pad:

Typical Properties	Value	Method	Uni
Hardness	68	ISO 48	°
Density	1.38	ISO 2781	g/cm <sup>3</sup>
Tensile Strength	11.0	ISO 37	kg/cm <sup>2</sup>
Elongation at Break	120	ISO 37	%
Temperature Range	-50°C to +120°C (+150°C intermittent)		°C

The information contained on this product information sheet is to be used as guidance. The advice is given in good faith and does not constitute any guarantee or recommendation for suitability. The Rubber Company cannot be held liable for any damage caused by incorrect installation. We hereby reserve the right to change the technical information herewith without notification or prior agreement.

### TICO® VHT:

Typical Properties	Value	Method	Uni
Hardness	60 ± 10	ISO 48	°
Density	1.15	ISO 2781	g/cm <sup>3</sup>
Tensile Strength	4.0 minimum	ISO 37	kg/cm <sup>2</sup>
Elongation at Break	300 minimum	ISO 37	%
Temperature Range	-60°C to +300°C		°C

The information contained on this product information sheet is to be used as guidance. The advice is given in good faith and does not constitute any guarantee or recommendation for suitability. The Rubber Company cannot be held liable for any damage caused by incorrect installation. We hereby reserve the right to change the technical information herewith without notification or prior agreement.