

High Grade EPDM Rubber Sheet – Peroxide Cured

Product Code: RC0302-PC

Product Description

A peroxide cured high grade EPDM rubber produces very stable carbon to carbon bonds, which results in superior material stability. This creates a material that performs better at higher temperatures as well as providing superior resistance to heat ageing and compression set.



Available In -



Full Rolls

Cut to strip

Bespoke Gaskets

Technical Specification

| Properties | Test Method | Values |
|------------------------------|-------------|---------------------------------|
| Product | | High Grade EPDM Rubber Sheeting |
| Compound | | EPDM |
| Hardness (Shore A) | | 70° ± 5° |
| Density | | 1.22 g/cm ² |
| Tensile Strength | | 9 N/mm ² |
| Elongation at Break | | 200% |
| Compression Set (22h, 100°C) | DIN ISO 815 | 25% |
| Working Temperature Range | | -40°C to + 120°C |



The information contained on this product information sheet is to be used as guidance. The advice is given in good faith and does not constitute any guarantee or recommendation for suitability. The Rubber Company cannot be held liable for any damage caused by incorrect installation. We hereby reserve the right to change the technical information herewith without notification or prior agreement.

Standard Sizes

| Properties |
|--------------------|
| 0.5mm x 1.4m x 20m |
| 1mm x 1.4m x 20m |
| 1.5mm x 1.4m x 20m |
| 2mm x 1.4m x 20m |
| 3mm x 1.4m x 10m |
| 4mm x 1.4m x 10m |
| 5mm x 1.4m x 10m |
| 6mm x 1.4m x 10m |
| 8mm x 1.4m x 5m |
| 10mm x 1.4m x 5m |
| 12mm x 1.4m x 5m |
| 15mm x 1.4m x 5m |
| 20mm x 1.4m x 5m |
| 25mm x 1.4m x 5m |
| 30mm x 1.4m x 5m |
| 40mm x 1.4m x 5m |



The information contained on this product information sheet is to be used as guidance. The advice is given in good faith and does not constitute any guarantee or recommendation for suitability. The Rubber Company cannot be held liable for any damage caused by incorrect installation. We hereby reserve the right to change the technical information herewith without notification or prior agreement.