

RubbaCrumb® 55° Shore Rubber Sheeting

Product Code: RC04197

Technical Specification

Properties	Value
Material	High Grade SBR rubber granulate bonded with polyurethane
Application	Impact sound insulation - acoustic underlay for flooring applications
Density EN ISO 845	730 Kg/m +/- 5% Weight/m ² 7.3kg
Thickness	3 - 10mm ± 0.3mm
Dimensions	10m x 1.25m or Cut Sheets/Parts
Dimension Tolerance DIN 7715 - 2 M4	± 1.5%
Tensile Strength DIN EN ISO 1798	>0.70Nmm ² at 10mm
Elongation at Break EN ISO 1798	>65% @ 10MM
Footfall Sound Insulation EN ISO 140-8	21db at 3 and 5mm, under 7mm standard laminate flooring
Dynamic Stiffness EN 29052-1 Measurement Executed in Deviation to Norm EN 29052/1- Without applying plaster on the test piece	77MN/m ³ in 3mm 70MN/M ³ in 4mm 63MN/m ³ in 5mm
Stress - Strain Characteristics in Compression EN ISO 3386-2	at 10mm (40x40x10mm) C24 ca.647 kPa 0.65Nmm ² C40 ca.2240 kPa 2.24Nmm ² C50 ca.5500 kPa 5.50Nmm ²
Load Deformation (Adapted from DIN EN ISO 3386-2)	Sample: 40 x 40 x 10mm 10% ca 145 kPa 15% ca 235 kPa 20% ca 360 kPa
Fire Classification EN 13501-1	E fl or equivalent to BS (DIN 4102)
Temperature Stability	-30°C to +100°C
Date of Issue	10/2018

The information contained on this product information sheet is to be used as guidance. The advice is given in good faith and does not constitute any guarantee or recommendation for suitability. The Rubber Company cannot be held liable for any damage caused by incorrect installation. We hereby reserve the right to change the technical information herewith without notification or prior agreement.